

SUZORITE® 25-Z

IMERYS Suzorite® 25-Z phlogopite mica is a blended product which is processed in Boucherville, Quebec.

Manufacturers specify phlogopite mica for applications requiring reinforcement and where greater resistance to moisture, heat, light or chemicals is needed. As a platy mineral, Imerys phlogopite mica offers beneficial rheological properties, is chemically inert, and provides the highest thermal stability of any mica. These properties render Imerys phlogopite micas excellent functional minerals for plastic composites, sound deadening, foundry coatings, and many other applications.

IMERYS Suzorite 25-Z mica has a high aspect ratio and is used in a broad range of applications, including:

- Oil Well Drilling: Promotes circulation of drill and material, fills pores in drilling holes, and reduces voids in circumferentially drilled media.
- Brake Pads: Provides heat resistance for rotor and drum, while being less abrasive than metals. Also reduces brake noise.

TYPICAL PROPERTIES

Source	Boucherville, Quebec, Canada
Sieve Analysis (wt. % Retained)	Typical Value
+10	31
-10 / +20	56
-20	13
Moisture (@100° C) (wt.%)	0.5
Density:	
Bulk (lbs/ft. ³)	50
Specific Gravity	2.73
Loss On Ignition (@ 1000°C) (wt.%)	<1.0
pH	9.2
Hardness (Mohs)	3
Refractive Index	1.58
Dielectric Constant	7.5



PROCESSEUR MEMBRE DU
PANTHON AUSTRALIEN



July 2012
©IMERYS 2012
Sixth Edition
All products are registered
trademarks of IMERYS

CAS No. 12001-26-2

IMERYS
100 Mansell Court East
Suite 300
Roswell, GA 30076

General:
Tel: (770) 594.0660
Fax: (770) 645.3384
www.imerys-perfmins.com

Customer Service:
Tel: (888) 277.9636
Fax: (770) 645.3631

IMERYS is a business name of
IMERYS Pigments, Inc.,
IMERYS Kaolin, Inc.,
IMERYS Mica Suzorite, Inc.
and IMERYS Marble, Inc.
Registered in the USA.

This information is
believed to be correct.
However, this information
does not constitute any
representation, condition or
warranty, nor do
we guarantee results
to be obtained. All
recommendations and
sales are made on the condition
that we will not be held liable for
any damages resulting from their
use. This provision may
not be changed by any
of our representatives.